
















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		5/64e loop pile
Tuft Density	ISO 1763	202 800 Stitches/m ²
Total Pile Mass	ISO 8543	710 g/m ²
Mass of Pile above the Substrate	ISO 8543	380 g/m ²
Thickness of Pile above the Substrate	ISO 1766	3,0 mm
Surface Pile Density	ISO 8543	0,126 g/cm ³
Total Weight	ISO 8543	4660 g/m ²
Total Thickness	ISO 1765	7,0 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC1			
18 Colors	%	Fire rating EN 13501-1: BflS1 			
034	8,9%				
045	10,1%				
149	3,7%				
172	18,3%				
190	5,1%	Heated Floor  ISO 10456 0,09 m ² K/W	Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 23 dB		
200	20,0%				
031	19,0%				
039	7,1%				
042	13,0%	Electrostatic prop.  ISO 6356 ≤ 2,0kV ISO 10965 RT ≤ 10 ¹⁰ Ω	Sound Absorption  ISO 11654 α _w = 0,15 (H)		
171	26,4%				
180	28,5%				
195	7,0%	Dimensional Stability  EN 986 ≤ 0,10%	Color Fastness  EN 105 - B02 7/8		
034	8,6%				
045	10,0%				
149	4,8%	 N° 0679-CPR-0196 07 EN 14041: 2004	Castor Chair  EN 985 Passed R≥2,4		
172	12,2%				
190	5,1%				
210	14,8%				



The above information is subject to modifications for the benefit of further improvement. (Updated on 07/09/2017)