


Kingston


Technical Specifications

Style Name	Kingston
Construction	Multi-Level Loop
Fiber	100% Nylon
Gauge	1/12"
Stitches	12 per inch
Pile Weight	20 OZ/yd ²
Average Pile Height	4 mm±0.5 mm
Backing	Mix-bac
Tile Size	50cm*50cm
Anti-microbial	Ultra-Fresh (Available)
Installation Method	



Performance Specifications

	Test Code	Standard	Test Results
Flammability Tests			
Radiant Panel	ASTM E 648	≥45 watt/cm	Class I
Methenamine Pill	ASTM D2859	7 out of 8	8
Smoke Density	ASTM E 662	≤ 450 DMC	≤ 450
Stability			
Delamination	ASTM D3936	≥ 3.0 lbc/in	No Separation
Dimensional Stability	AACHEN	≤ 0.2%	≤ 0.2%
Tuft Bind	ASTM D1335	≥ 8.0 lbs	≥ 8.0 lbs
Anti-Static			
Static Propensity	AATCC 134	≤ 3.5 kV	≤ 3.5 kV
Colour Fastness			
Light	AATCC 16 E	≥ 4-5	4-5
Rubbing/Crocking	AATCC 165	≥ 4-5	4-5
Wear Tests			
Castor Chair	BS EN 985	r ≥ 2.4	r = 2.8
Hexapod Drum	ASTM D5252	≥ 3-4	3
Generic Tests			
Green Carpet(VOC)	CRI Green Label GLP 6331 [#] /6332 [#]		Accredited
Acoustic-Nylon	BS EN ISO 354	Absorption Coefficient-NRC	aw =0.15(H)



Declare.



LIVING BUILDING CHALLENGESM



3R Reduce Reuse Recycle
= Infinity Green!

