

DESCRIPTION

Total thickness	EN 428	mm	2.00
Weight	EN 430	g/sq.m	2460
Thickness of Wearlayer	EN 429	mm	0.85
Width/Length of Sheet	EN 426	m/lm	2/20

CLASSIFICATION

European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	AS ISO9239-1	kW/m2	8.3
		smoke%/min	134
Slip resistance - Wet Pendulum	AS 4586-2013 (App A)	class	P3
Slip resistance - Wet/Barefoot Ramp	AS 4586-2013 (App C)	class	A
Slip resistance - Oil Wet Ramp	AS 4586-2013 (App D)	class	R10
Surface roughness	-	µm	Rz≥20
Electrical resistance	EN 1815	kV	< 2



PERFORMANCE

Abrasion resistance	EN 660.2	mm ³	≤ 2.0
Abrasion Group	EN 651	group	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	c 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≤ 6
Surface treatment	-	-	SparClean®
Chemical products resistance	EN 423	class	Good

ENVIRONMENT / INDOOR AIR QUALITY

VOC	ASTM D5116	mg/m2/hr (24hours)	< 0.018
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	
---	----------	---	---

Gerflor has a policy of continuous product and product data improvement, it reserves the right to change design and specifications without notice.