



Infrastructure Technologies

37 Graham Road (PO Box 56), Highett, Victoria, Australia 3190

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <http://www.cmse.csiro.au>

Registered Testing Authority - CSIRO

17 November 2015

Our Ref. EN13 / 415 03/0212

TEST REPORT No. 7538

Requested by: Gerflor Australasia P/L
 17 Cato St
 Hawthorn East
 VIC 3123

on (date): 27 October 2015

Manufacturer: Gerflor

Product Desc.: Mipolam Ambiance Ultra

Sampling details:

Where: Delivered

Date: 27 October 2015

By whom: Courier

How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 4 pages

SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS 4586:2013	Slip resistance classification of new pedestrian surface materials Appendix A: WET Pendulum (Slider 96):		
	Mean SRV:	45	P4
AS 4586:2013	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET Ramp		
	Corrected mean overall acceptance angle:	6°	R 9

In order to interpret the classifications, please refer to Standards Australia Handbook 198, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: 7538
ISSUE DATE: 17 November 2015
MANUFACTURER: Gerflor
PRODUCT DESC: Mipolam Ambiance Ultra

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

WET PENDULUM TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix A)

Test Date: 4 November 2015

RESULTS: Location: Slip Resistance Laboratory Slider used: 96
Conditioned with grade P400 paper, dry
and Imperial Lapping Film Grade 3MIC, wet
Sample: Unfixed
Cleaning: Deionized water
Temperature: 23.6°C

Pendulum Friction Tester: Stanley (S/N: 0312, calibrated 03/06/2014)
Test conducted by: Khanh Ho

	Specimen				
	1	2	3	4	5
Last 3 swings (BPN)	48	49	41	44	44
	47	49	41	45	44
	47	48	41	44	44
Averages	47	49	41	44	44

Mean SRV : 45

CLASS :

P4

Where products are to be used in wet barefoot areas, it is more appropriate to test to Appendix C of AS 4586 (which is technically equivalent to DIN 51097).



REPORT NO: 7538
ISSUE DATE: 17 November 2015
MANUFACTURER: Gerflor
PRODUCT DESC: Mipolam Ambiance Ultra

Page 3 of 4

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

OIL-WET RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix D)

Test Date: 17 November 2015

Location: Slip Resistance Laboratory Test conducted by: KH, AG

Sample Fixed

Joint width: 0 mm

Surface structure: Smooth
 Profiled
 Structured

RESULTS

Corrected mean overall acceptance angle: 6 °

Displacement space: not tested

CLASSIFICATION:

Slip Resistance Assessment Group:

R 9

Displacement Space Assessment Group:

-

Test shoe used: Uvex Athletic



Infrastructure Technologies

37 Graham Road (PO Box 56), Highett, Victoria, Australia 3190

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Web: <http://www.cmse.csiro.au>

REPORT NO: 7538
ISSUE DATE: 17 November 2015
MANUFACTURER: Gerflor
PRODUCT DESC: Mipolam Ambiance Ultra

Page 4 of 4

Date and Place 17 November 2015, Highett, Vic

Name, Title and Digital Signature:

A digital signature in black ink, appearing to be 'Khanh Ho', is written over a semi-transparent grey circular watermark of the CSIRO logo.

KHANH HO
Technical Officer
Tel: 61 3 92526119
Fax: 61 3 92526244
Email: Khanh.Ho@csiro.au
