
TARASAFE ULTRA

Advance Flooring Systems

2 m | 2 m COMFORT | 16 dB COMFORT | Heavy traffic | R10 SLIP RESISTANT | HSE 36+ SLIP RESISTANT | SparClean® TREATED

0508 238 262


High performance vinyl safety flooring for contract applications



8701 Opal
LRV: 59.1 - WR: 0603

Performances and benefits


- Brighter, cleaner crystal particles that add real sparkle
- High resistance to heavy traffic
- Matt finish for an improved design experience
- Easier to cut-up 5 times more blade life
- Easier to install, lighter & more flexible to handle




7482 Halite
LRV: 32.5 - WR: 0500




8704 Pebble
LRV: 44.1 - WR: 0173



7383 Diopside
LRV: 59.6 - WR: 2416




4323 Sandstone
LRV: 51.5 - WR: 2350




4463 Aqua
LRV: 35.1 - WR: 2668




8709 Granite
LRV: 25.4 - WR: 0033



7384 Citrine
LRV: 40.2 - WR: 2174




4505 Peridot
LRV: 35.5 - WR: 2499




4465 Cobalt
LRV: 23.6 - WR: 0190



8710 Basalt
LRV: 11.9 - WR: 2530




8013 Jasper
LRV: 23.5 - WR: 2282




4508 Jade
LRV: 26.1 - WR: 2418




4472 Moonstone
LRV: 12.6 - WR: 0905




8717 Obsidian
LRV: 10.1 - WR: 2238



4128 Ruby
LRV: 13.8 - WR: 2947



4460 Topaz
LRV: 23 - WR: 2434



4470 Sapphire
LRV: 17.1 - WR: 2165

Comfort sheet with foam backing - Compact sheet without foam backing

Colour reference available as **TARASAFE ULTRA H20**

Ask for the **Tarasafe Ultra H20** sample card!

LRV: Light Reflectance Value

WR: Welding Rod = 0585 + colour code number

* For more details visit the greenguide.org.uk

IN YOUR LOCAL DISTRIBUTOR NOW!

Gerflor® theflooringgroup

SAFETY FLOORING

gerflor.com

TARASAFE ULTRA & ULTRA COMFORT are slip resistant safety vinyl floorcoverings, with a PVC wear layer and deeply **inlaid mineral crystal particles** (patented) and coloured chips for a decorative design. They are reinforced with a glass fibre grid and are available in a sheet format.
The ranges are ideal for **heavy traffic applications** where slip resistance, durability, hygiene and easy maintenance are required. Suitable for most contract & commercial areas, they are a popular choice in the education and healthcare environments, the matt finish surface is also perfectly suitable for dementia care units.
They are eco-friendly, 100% recyclable, Floorscore® certified and do not contain any heavy metals or CMR 1&2. They are also 100% compliant with REACH.
The product emission rate of volatile organic compounds is < 100 µg/m³ (TVOC after 28 days – ISO 16000 -6).
The SparClean® surface treatment improves the product performance in terms of stain and dirt resistance and designs last longer for extended durability.
TARASAFE ULTRA COMFORT has a VHD closed cell foam backing yielding a 16dB sound insulation.

			Tarasafe Ultra	Tarasafe Ultra Comfort
DESCRIPTION				
Total Thickness	EN ISO 24346 (EN 428)	mm	2.0	3.2
Thickness of wearlayer	EN ISO 24340 (EN 429)	mm	0.85	0.85
Weight	EN ISO 23997 (EN 430)	g/sq.m	2460	2960
Width/Length of Sheet	EN ISO 24341 (EN 426)	cm/lm	200/20	200/20
CLASSIFICATION				
Norm/Product Specification	-	-	EN ISO 10582 (EN 649)	EN 651
European classification	EN ISO 10874 (EN 685)	class	34-43	34-42
Fire Rating	EN 13501-1	class	Bfl-s1	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2	< 2
Slip resistance: Pendulum Test (dry & wet)	BS 7976-2	PTV	> 36	-
Surface roughness Rz	-	µm	⩾ 20	-
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10	R10
Slip resistance wet: ramp test with water	DIN 51 097	class	B	-
Slip resistance – ramp test	EN 13845 (annex C)	class	ESf-ESb	-
PERFORMANCE				
Wear Resistance	EN 660.2	mm³	⩽ 2	⩽ 2
Wear group	NF 189	group	T	T
Type binder content	EN ISO 10582	type	I	-
Dimensional stability	EN ISO 23999 (EN 434)	%	⩽ 0.40	⩽ 0.40
Residual indentation	EN ISO 24343-1 (EN 433)	mm	⩽ 0.03	⩽ 0.20
Impact sound insulation	EN ISO 717-2	dB	-	16
Castor Chair test (type W)	ISO 4918 (EN 425)	-	OK	OK
Thermal Conductivity	EN ISO 10456 (EN 12524)	W/(m.K)	0.25	0.25
Colour Fastness	EN 20 105-B02	degree	⩾ 6	⩾ 6
Surface Treatment	-	-	SparClean®	SparClean®
Chemical Products Resistance	EN ISO 26987 (EN 423)	-	OK	OK
Anti-bacterial activity (MRSA) (1)	ISO 22196	-	> 99% Inhibits growth	> 99% Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000-6	µg/m³	< 100	
Certification	-	-	Floorscore®	
CE MARKING				
CE	EN 14 041	-		

(1) The implementation of an effective cleaning method is the best defence against infection.

UK reference

Installation and Maintenance Guidelines, Complementary ranges available on our Gerflor website.

IMPORTANT: The information contained in this document is valid from 1/01/2018 and is subject to change at any time without notice. In the context of constantly changing technology, our customers are responsible, prior to any use, for checking with us that this document is the version in force.

Rubber leaves indelible stains on vinyl floorings: do not use mats with rubber backing and replace tubular furniture feet with those made of PVC or polyamide. Place mats of sufficient length at entrances to reduce outside sources of dirt.

TARASAFE ULTRA, **LESS SPEAKING FOR MORE ACTIONS**

COMPOSITION
100 % REACH

INDOOR AIR QUALITY
10 times lower than norms requirements (TVOC < 100 ug/m³ after 28 days)

RECYCLABILITY
100 %

LCA
Eco-designed according to a product specific life cycle analysis

WELLNESS
Anti slip R10

Advance Flooring Systems

Gerflor® theflooringgroup

Création : misterBrown - Réalisation : coco & co - Z0012401 - 02/2019 - Indicative documentation cost: 2.00 €