



# Confidential Report

**Our Ref: 25/10431C-Supp/11/20**



1066

Notified Body  
for PPE Directive,  
Construction Products Regulation  
& Marine Equipment Directive  
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 1 of 8

**Client:** **Voxflor Industrial Park Co. Ltd**

27/F Central Park Building No. 868  
Changshou Road  
Shanghai  
200060  
China

**Job Title:** Fire Test on One Sample of Carpet Tiles

**Clients Order Ref:** ---

**Date of Receipt:** 09 November 2020

**Description of Sample:** One sample of carpet tiles,  
Sample Project: Voxflor China Tests in Europe  
Sample Reference: Fibre Nylon  
Backing: EcoAce-Bac


**Work Requested:** We were asked to make the following test(s):

BS EN 13501-1 (tested loose laid)

This is a supplementary report to the one issued on the 30<sup>th</sup> November 2020 under our report reference 25/10431C/11/20

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 2 of 8

Client: Voxflor Industrial Park Co. Ltd

## **FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2010**

### **Reaction to fire tests for building products – Part 2:**

### **Ignitability when subjected to direct impingement of flame**

Date of Test: 20/11/2020

## **Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

## **Procedure**

The sample was tested in accordance with BS EN ISO 11925-2:2010.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

1. If ignition occurs
2. Presence of flaming debris, if applicable
3. Ignition of the filter paper, if applicable

## **Duration of test**

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 3 of 8

**Client: Voxflor Industrial Park Co. Ltd**

## Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification	
Classification	Criteria (mean values)
E <sub>FL</sub>	F <sub>s</sub> ≤ 150mm within 20 seconds
F <sub>FL</sub>	None ( No performance determined)

Flaming droplets / particles classification	
Classification	Criteria
No classification	Pass
d2	Fail (Ignition of paper)

## Results

Specimen	Ignition (Yes or No)	Tip of flame reaches 150mm		Flaming droplets		
		Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)	
Machine Direction	1	Yes	No	N/A	No	No
	2	Yes	No	N/A	No	No
	3	Yes	No	N/A	No	No
Across Machine Direction	1	Yes	No	N/A	No	No
	2	Yes	No	N/A	No	No
	3	Yes	No	N/A	No	No

## Note

The specimens of floor covering were tested loose laid over a 12mm calcium silicate board , as defined in BS EN 13238:2010.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 4 of 8

Client: Voxflor Industrial Park Co. Ltd

## FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010

### Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 20/11/2020

## Conditioning

The specimens were conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of  $(6\pm 1)$ mm and a density of  $(1,800\pm 200)$  Kg/m<sup>3</sup> representing the standard substrate of Class A1fl or A2fl.

## Procedure

The test was carried out in accordance with BS EN ISO 9239-1:2010. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m<sup>2</sup> to 1.0 kW/m<sup>2</sup> along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, whichever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
 Telephone: +44 (0) 113 259 1999  
 Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
 : [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
 Your Ref: ---

Page: 5 of 8

**Client:** Voxflor Industrial Park Co. Ltd

## Classification Criteria

The samples were classified according to BS EN 13501-1:2007+A1:2009 - Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m <sup>2</sup> )
Bfl	8.0
Cfl	4.5
Dfl	3.0
	Smoke Production % x min
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2010 the sample has to have a flame spread (Fs) of: Fs ≤ 150mm within 20 seconds (Class Efl).

## Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
 Telephone: +44 (0) 113 259 1999  
 Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
 : [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
 Your Ref: ---

Page: 6 of 8

Client: **Voxflor Industrial Park Co. Ltd**

## Results (Continued)


<u>Specimen No.</u>	<u>Direction of specimen</u>	<u>Smoke Obscuration</u>		<u>Maximum Flame front (mm)</u>	<u>Critical Heat Flux (kW/m<sup>2</sup>)</u>	<u>Duration of Flaming (sec)</u>
		<u>Max %</u>	<u>% x min</u>			
1	Machine	11	41	190	9.2	811
2	Across	12	40	201	9.1	900
3	Across	12	38	231	8.5	905
4	Across	23	121	240	8.3	870
Mean of 3 specimens	Across	16	66	224	8.6	892

<u>Distance Burnt (mm)</u>	<u>Time for each specimen to burn (s)</u>			
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
50	184	175	213	165
100	245	240	255	210
150	360	310	360	290
200	---	740	480	430
250	---	---	---	---

## Note

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested loose laid over a 12mm calcium silicate board, as defined in BS EN 13238:2010.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
 A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
 BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
 The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
 Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 7 of 8

Client: **Voxflor Industrial Park Co. Ltd**

## Comment

The results meet the requirements of a **Class B<sub>fl</sub>-s1**, as specified in BS EN 13501-1:2007+A1:2009.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Enquiries concerning this report should be addressed to Customer Services.

Reported by:.....*B Marsden*..... B Marsden (Mrs), Senior Fire Technician

Countersigned by:.....*P Doherty*..... P Doherty, Executive Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 11 January 2020

Our Ref: 25/10431C-Supp/11/20  
Your Ref: ---

Page: 8 of 8

Client: Voxflor Industrial Park Co. Ltd

## Uncertainty Budget - Annex

The uncertainty budget for BS EN 13501-1:2007 + A1:2009 was determined as follows:-

### BS EN ISO 11925-2:2010

Distance  $\pm 3$ mm, rest operator dependant but fully notable

### Overall (BS EN ISO 9239-1)

The uncertainty varies, therefore:

At position between a Euroclass B to C  $\pm 15\%$

At position between a Euroclass C to D  $\pm 15.5\%$

At position between a Euroclass D to E  $\pm 17.5\%$



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.