



Wira House  
West Park Ring Road  
Leeds, LS16 6QL

Tel: +44 (0)113 259 1999  
Fax: +44 (0)113 278 0306  
Web: <http://www.bttg.co.uk/bctc>  
Email: [CSLeeds@bttg.co.uk](mailto:CSLeeds@bttg.co.uk)

Our Ref: 2600829B/01/09  
Your Ref:  
Order No:

10 February 2009  
Page 1 of 7

Client: CTTCC  
Jiangxi Huateng Carpet International Park Co. Ltd  
Dongxing Road  
High and New Technology Development Zone  
Xinyu  
Jiangxi Province, 338000  
China

Job Title: **Fire Test on One Sample of Carpet Tiles**

Material Received: 5 January 2009

Description of Sample: One sample of carpet tiles referenced, **Block, 100% Nylon.**

Brief: BCTC were requested to carry out a fire test on the sample supplied according to BS EN ISO 13501.

UKAS Accreditation: Our Laboratories are UKAS accredited. However, it should be noted that tests marked \* are not UKAS accredited in this report. They are not included in the UKAS Accreditation Schedule for our laboratory, either due to the work not conforming fully to the standard (e.g. reduced number of specimens) or to it being outside the scope of our accreditation, or subcontracted.

Uncertainty: An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Testing Atmosphere: Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles (BS EN ISO 139:2005) of 65±4% r.h. and 20±2°C.



Date: 10 February 2009  
Our Ref: 2600829B/01/09  
Your Ref:  
Order No:  
Page 2 of 7

CTTCC

**FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2002**  
**Reaction to fire tests for building products – Part 2:**  
**Ignitability when subjected to direct impingement of flame**

**Date of Test: 09/02/2009**

**Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2001.

**Procedure**

The sample was tested in accordance with BS EN ISO 11925-2:2002.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

1. If ignition occurs
2. Presence of flaming debris, if applicable
3. Ignition of the filter paper, if applicable

**Duration of test**

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.

**Classification Criteria**

The samples were classified according to BS EN 13501:2002 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification	
Classification	Criteria (mean values)
E <sub>FL</sub>	F <sub>s</sub> ≤ 150mm within 20 seconds
F <sub>FL</sub>	None ( No performance determined)

Flaming droplets / particles classification	
Classification	Criteria
No classification	Pass
d2	Fail (Ignition of paper)

**Results**

	<u>Ignition</u> (Yes or No)	<u>Time of flaming if ignition occurs (s)</u>	<u>Tip of flame reaches 150mm</u> Yes or No	<u>Time taken (s)</u>	<u>Flaming droplets Ignition of Filter paper (Yes or No)</u>	<u>Classification</u>
Warp 1	No	---	No	---	No	E <sub>FL</sub>
Warp 2	No	---	No	---	No	E <sub>FL</sub>
Warp 3	No	---	No	---	No	E <sub>FL</sub>
Weft 1	No	---	No	---	No	E <sub>FL</sub>
Weft 2	No	---	No	---	No	E <sub>FL</sub>
Weft 3	No	---	No	---	No	E <sub>FL</sub>



Date: 10 February 2009  
Our Ref: 2600829B/01/09  
Your Ref:  
Order No:  
Page 4 of 7

CTTCC

## **FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2002**

**Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2002)**

**Date of Test: 09/02/2009**

### **Conditioning**

The specimens were conditioned in accordance with BS EN 13238:2001. The substrate used was a fibre cement board (ISO 390) with a thickness of  $(6 \pm 1)$ mm and a density of  $(1,800 \pm 200)$  Kg/m<sup>3</sup> representing the standard substrate of Class A1fl or A2fl.

### **Procedure**

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimens to the dimensions stated.

Specimens were individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11.0 kW/m<sup>2</sup> to 1.0 kW/m<sup>2</sup> along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, whichever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.



Date: 10 February 2009  
Our Ref: 2600829B/01/09  
Your Ref:  
Order No:  
Page 5 of 7

CTTCC

### Classification Criteria

The samples were classified according to BS EN 13501:2002: Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For floorings, including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m <sup>2</sup> )
B <sub>fl</sub>	8.0
C <sub>fl</sub>	4.5
D <sub>fl</sub>	3.0
	Smoke Production % x min
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2002 the sample has to have a flame spread (Fs) of:  $F_s \leq 150\text{mm}$  within 20 seconds (Class E<sub>fl</sub>).

### Results

The test results relate to the behaviour of the test specimens of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.



CTTCC

**Results (Continued)**

<u>Specimen No.</u>	<u>Direction of specimen</u>	<u>Smoke Obscuration</u>		<u>Maximum Flame front (mm)</u>	<u>Critical Heat Flux (kW/m<sup>2</sup>)</u>	<u>Duration of Flaming (sec)</u>
		<u>Max %</u>	<u>% x min</u>			
1	Machine	46	261	240	8.2	930
2	Across	58	402	485	3.5	1800 ME
3	Across	60	455	465	3.9	1800 ME
4	Across	52	272	235	8.3	803
Mean of 3 specimens	Across	57	376	395	5.2	1468

ME Manually Extinguished

<u>Distance Burnt (mm)</u>	<u>Time for each specimen to burn (s)</u>			
	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
50	193	150	170	180
100	257	208	249	217
150	319	249	334	275
200	418	297	406	405
250	---	488	509	---
300	---	600	669	---
350	---	900	917	---
400	---	1114	1200	---
450	---	1462	1620	---

**Note**

One specimen was initially tested in each direction and whichever direction gave the worst result a further two specimens were tested. Only the results of the 3 specimens in the same direction were used to calculate the mean results.

The specimens of floor covering were tested loose laid onto a 12mm calcium silicate board as defined in BS EN 13238:2001.



Date: 10 February 2009  
Our Ref: 2600829B/01/09  
Your Ref:  
Order No:  
Page 7 of 7

CTTCC

**Comments**

The results indicate that the sample meets an overall classification of: **Class C<sub>fl</sub>-s1**.

The information contained on page no's 1/7 of this certificate is hereby certified to be a correct statement of the tests and investigations carried out by the British Carpet Technical Centre on the materials referred to.

Signed.....*B. Marsden*.....Date..... 11 February 2009  
Mrs B Marsden  
Fire Technician

Reported By.....*P. Doherty*.....Date..... 11 February 2009  
P Doherty  
Operational Head

