

















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution dyed)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	196 800 Stitches/m ²
Total Pile Mass	ISO 8543	500 g/m ²
Mass of Pile above the Substrate	ISO 8543	290 g/m ²
Thickness of Pile above the Substrate	ISO 1766	2,6 mm
Surface Pile Density	ISO 8543	0,111 g/cm ³
Total Weight	ISO 8543	4270 g/m ²
Total Thickness	ISO 1765	6.3 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC1		
11 Colors	%			
023	10,3%	 Classement UPEC NF 262 - U3P3E1C0 (certificate n° 349T-001.1)		 Fire rating EN ISO 9239-1 8.6kW/2
028	3,9%			
032	18,2%	Heated Floor  ISO 10456 0,08 m² K/W	Impact Noise Reduction  EN ISO 10143-3 $\Delta L (w) 24 \text{ dB}$	
036	11,9%			
038	7,2%	Electrostatic prop.  ISO 6356 $\leq 2,0\text{kV}$	Sound Absorption  ISO 11654 $\alpha_w = 0,15 (H)$	
048	9,6%	ISO 10965 $RT \approx 10^{10}\Omega$		
056	17,9%	Dimensional Stability  EN 986 $\leq 0,10\%$	Color Fastness  EN 105 - B02 7/8	
062	21,9%			
068	15,9%	 N° 0679-CPR-0196	Castor Chair  EN 985 Passed R \geq 2,4	
088	5,5%		07	
097	7,5%		EN 14041: 2004	



The above information is subject to modifications for the benefit of further improvement. (Updated on 29/03/2017)