
















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		5/64e loop pile
Tuft Density	ISO 1763	223 600 Stitches/m ²
Total Pile Mass	ISO 8543	850 g/m ²
Mass of Pile above the Substrate	ISO 8543	520 g/m ²
Thickness of Pile above the Substrate	ISO 1766	3,5 mm
Surface Pile Density	ISO 8543	0,149 g/cm ³
Total Weight	ISO 8543	4800 g/m ²
Total Thickness	ISO 1765	7,5 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV				Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC2			
8 Colors	%	Fire rating EN 13501-1: BflS1 					
030	15,8%						
130	20,5%						
139	11,9%						
140	19,4%	Heated Floor  ISO 10456 0,10 m ² K/W		Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 25 dB			
182	27,5%	Electrostatic prop.  ISO 6356 ≤ 2,0kV		Sound Absorption  ISO 11654 α _w = 0,20 (H)			
209	12,5%	ISO 10965 RT ≥ 10 ¹⁰ Ω		Color Fastness  EN 105 - B02 7/8			
240	14,1%	Dimensional Stability  EN 986 ≤ 0,10%		Castor Chair  EN 985 Passed R≥2,4			
340	14,8%	 N° 0679-CPR-0196 07 EN 14041: 2004					



The above information is subject to modifications for the benefit of further improvement. (Updated on 01/09/2017)