
















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		5/64e loop pile
Tuft Density	ISO 1763	223 600 Stitches/m ²
Total Pile Mass	ISO 8543	885 g/m ²
Mass of Pile above the Substrate	ISO 8543	500 g/m ²
Thickness of Pile above the Substrate	ISO 1766	4 mm
Surface Pile Density	ISO 8543	0,125 g/cm ³
Total Weight	ISO 8543	4835 g/m ²
Total Thickness	ISO 1765	7,7 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC2		
10 Colors	%			
030	14,8%	Fire rating EN 13501-1: BflS1 		
130	24,0%			
139	14,8%			
140	9,2%	Heated Floor  ISO 10456 0,10 m ² K/W	Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 25 dB	
171	23,7%			
182	28,6%	Electrostatic prop.  ISO 6356 ≤ 2,0kV	Sound Absorption  ISO 11654 α _w = 0,20 (H)	
209*	11,0%	ISO 10965 RT ≈ 10 ¹⁰ Ω		
230	18,5%	Dimensional Stability  EN 986 ≤ 0,10%	Color Fastness  EN 105 - B02 7/8	
240	12,6%			
340	7,4%	 N° 0679-CPR-0196 07 EN 14041: 2004	Castor Chair  EN 985 Passed R≥2,4	



The above information is subject to modifications for the benefit of further improvement. (Updated on 01/09/2017)