

















**Specifications**

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	143 500 Stitches/m <sup>2</sup>
Total Pile Mass	ISO 8543	510 g/m <sup>2</sup>
Mass of Pile above the Substrate	ISO 8543	300 g/m <sup>2</sup>
Thickness of Pile above the Substrate	ISO 1766	3.0 mm
Surface Pile Density	ISO 8543	0,100 g/cm <sup>3</sup>
Total Weight	ISO 8543	3740 g/m <sup>2</sup>
Total Thickness	ISO 1765	6.3 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m <sup>2</sup>
Installation		



Technical Performances

<b>RHO-LRV</b>				Classification EN 1307 - 23/32 / Commercial General Luxury Class – LC1		
12 Colors	%					
017	5,0%			Classement UPEC NF 262 - U3P3E1C0 (certificate n° 349T-008.1)		 Bfl-s1
024	9,0%			Fire rating EN 13501-1: BflS1		
026	5,1%					
028	3,9%	<b>Heated Floor</b> 		ISO 10456	0,09 m² K/W	<b>Impact Noise Reduction</b>  EN ISO 10143-3 ΔL (w) 25 dB
032	17,5%					
034	8,9%	<b>Electrostatic prop.</b> 		ISO 6356	≤ 2,0kV	<b>Sound Absorption</b>  ISO 11654 αw = 0,15 (H)
044	8,7%			ISO 10965	RT ≈ 10 <sup>10</sup> Ω	
045	5,3%	<b>Dimensional Stability</b> 		EN 986	≤ 0,10%	<b>Color Fastness</b>  EN 105 - B02 7/8
064	15,1%					
087	9,0%			N° 0679-CPR-0196		<b>Castor Chair</b>  EN 985 Passed R≥2,4
097	6,5%			07		
100	18,5%			EN 14041: 2004		



The above information is subject to modifications for the benefit of further improvement. (Updated on 29/03/2017)