

















## Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (Solution Dyed)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	143 500 Stitches/m <sup>2</sup>
Total Pile Mass	ISO 8543	510 g/m <sup>2</sup>
Mass of Pile above the Substrate	ISO 8543	300 g/m <sup>2</sup>
Thickness of Pile above the Substrate	ISO 1766	3.0 mm
Surface Pile Density	ISO 8543	0,100 g/cm <sup>3</sup>
Total Weight	ISO 8543	3740 g/m <sup>2</sup>
Total Thickness	ISO 1765	6.3 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m <sup>2</sup>
Installation		



Technical Performances

<b>RHO-LRV</b>		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC1				
4 Colors	%	 Classement UPEC NF 262 - U3P3E1C0 (Certificate n° 349T-008.1) Fire rating EN 13501-1 : Bfls1				 Bfl-s1
925	6,4%					
936	10,7%					
937	9,8%					
997	6,0%	<b>Heated Floor</b>  ISO 10456    0,09 m² K/W	<b>Impact Noise Reduction</b>  EN ISO 10143-3    ΔL (w) 25 dB			
<b>Electrostatic prop.</b>  ISO 6356    ≤ 2,0kV ISO 10965    RT ≈ 10 <sup>10</sup> Ω		<b>Sound Absorption</b>  ISO 11654    α <sub>w</sub> = 0,15 (H)				
<b>Dimensional Stability</b>  EN 986    ≤ 0,10%		<b>Color Fastness</b>  EN 105 - B02    7/8				
 N° 0679-CPR-0196 07 EN 14041: 2004		<b>Castor Chair</b>  EN 985    Passed R≥2,4				



The above information is subject to modifications for the benefit of further improvement. (Updated on 03/04/2017)