














Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (50% Solution dyed + 50% space dyed ECONYL Yarns)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	151 700 Stitches/m ²
Total Pile Mass	ISO 8543	520 g/m ²
Mass of Pile above the Substrate	ISO 8543	290 g/m ²
Thickness of Pile above the Substrate	ISO 1766	2.9 mm
Surface Pile Density	ISO 8543	0,100 g/cm ³
Total Weight	ISO 8543	4300 g/m ²
Total Thickness	ISO 1765	6.8 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV		 Classification EN 1307 - 23/32 / Commercial General Luxury Class – LC1			
20 Colors	%	 Classement UPEC NF 262 - U3P3E1C0 (Certificate n° 349T-002.1) Fire rating EN 13501-1 : Bfl-s1			
022	22,2%				
024	6,8%				
025	8,3%				
026	5,5%				
028	3,8%				
029	7,0%				
034	14,1%				
038	7,7%				
043	12,5%				
045	7,0%	Electrostatic prop.  ISO 6356 ≤ 2,0kV ISO 10965 RT ≈ 10 ¹⁰ Ω		Sound Absorption  ISO 11654 α _w = 0,15 (H)	
068	14,1%	Dimensional Stability  EN 986 ≤ 0,10%		Color Fastness  EN 105 - B02 5/8	
086	10,9%	 N° 0679-CPR-0196 07 EN 14041: 2004			
087	7,3%				
094	8,7%				
095	6,6%				
101	25,1%				
147	6,0%	Castor Chair  EN 985 Passed R≥2,4			
424	12,3%				
426	6,2%				
428	4,6%				



Répond à la démarche



The above information is subject to modifications for the benefit of further improvement. (Updated on 13/01/2017)