





Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (50% Solution dyed + 50% space dyed ECONYL Yarns)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	151 700 Stitches/m ²
Total Pile Mass	ISO 8543	520 g/m ²
Mass of Pile above the Substrate	ISO 8543	290 g/m ²
Thickness of Pile above the Substrate	ISO 1766	2.9 mm
Surface Pile Density	ISO 8543	0,100 g/cm ³
Total Weight	ISO 8543	4300 g/m ²
Total Thickness	ISO 1765	6.8 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV			Classification EN 1307 - 23/32 / Commercial General Luxury Class – LC1		
14 Colors	%				
016	4,7%		Classement UPEC NF 262 - U3P3E1C0 (Certificate n° 349T-002.1)		
017	4,5%		Fire rating EN 13501-1: BflS1		
022	10,9%				
023	7,2%	Heated Floor		Impact Noise Reduction	
024	6,6%	ISO 10456	0,09 m² K/W	EN ISO 10143-3	ΔL (w) 25 dB
025	6,9%				
026	5,2%	Electrostatic prop.		Sound Absorption	
035	7,4%	ISO 6356	≤ 2,0kV	ISO 11654	αw = 0,15 (H)
036	6,8%	ISO 10965	RT ≈ 10 ¹⁰ Ω		
038	5,7%	Dimensional Stability		Color Fastness	
047	6,8%	EN 986	≤ 0,10%	EN 105 - B02	≥ 5/8
087	8,0%		N° 0679-CPR-0196	Castor Chair	
094	6,6%		07	EN 985	Passed R≥2,4
195	5,4%		EN 14041: 2004		



The above information is subject to modifications for the benefit of further improvement. (Updated on 03/04/2017)