
















Specifications

DESCRIPTION	NORM	DATA
Pile Fiber		100% Polyamide (100% space dyed ECONYL Yarns)
Gauge		1/10 loop pile
Tuft Density	ISO 1763	155 800 Stitches/m ²
Total Pile Mass	ISO 8543	645 g/m ²
Mass of Pile above the Substrate	ISO 8543	360 g/m ²
Thickness of Pile above the Substrate	ISO 1766	3,1 mm
Surface Pile Density	ISO 8543	0,116 g/cm ³
Total Weight	ISO 8543	3870 g/m ²
Total Thickness	ISO 1765	6,5 mm
Primary Backing		Non-woven primary backing
Backing		Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Tile Size		50x50cm
Tiles per Box		20 = 5m ²
Installation		



Technical Performances

RHO-LRV		 Classification EN 1307 - 33 / Commercial Heavy Luxury Class – LC1			
12 Colors	%	 Classement UPEC NF 262 - U3P3E1C0 (Certificate n° 349T-009.1) Fire rating EN 13501-1 : BflS1			
025	7,0%				
031	21,4%				
032	13,1%				
035	7,5%	Heated Floor  ISO 10456 0,08 m² K/W		Impact Noise Reduction  EN ISO 10143-3 ΔL (w) 26 dB	
047	5,5%	Electrostatic prop.  ISO 6356 ≤ 2,0kV ISO 10965 RT ≤ 10 ¹⁰ Ω		Sound Absorption  ISO 11654 α _w = 0,15 (H)	
054	11,0%	Dimensional Stability  EN 986 ≤ 0,10%		Color Fastness  EN 105 - B02 ≥ 5/8	
076	11,2%	 N° 0679-CPR-0196 07 EN 14041: 2004		Castor Chair  EN 985 Passed R≥2,4	
084	15,8%				
097	6,9%				
115	5,5%				
145	6,2%				
172	27,4%				



The above information is subject to modifications for the benefit of further improvement. (Updated on 11/09/2017)