

DESCRIPTION

| | | | |
|------------------------|--------------------------|------------------|------|
| Total thickness | EN ISO 24346 (EN 428) | mm | 2.20 |
| Thickness of wearlayer | EN ISO 24340 (EN 429) | mm | 1.12 |
| Weight | EN ISO 23997 (EN 430) | g/m ² | 2880 |
| Width of sheet | EN ISO24341 (EN 426) | cm | 200 |
| Length of sheet | EN ISO24341 (EN 426) | ml | 20 |

CLASSIFICATION

| | | | |
|--|---------------------------------|--------|--------------------------|
| Norm / Product specification | - | - | EN ISO 10582 (EN 649) |
| European classification | EN ISO 10874 (EN 685) | classe | 34 - 43 |
| Fire rating | EN 13 501-1 | classe | B _{fl} -s1 |
| Static electrical propensity | EN 1815 | kV | < 2 |
| Slip resistance wet : ramp test with oil | DIN 51 130 | Classe | R12 |






PERFORMANCES

| | | | |
|--|-----------------------------|-----------------|--------------------------|
| Wear resistance | EN 660.2 | mm ³ | ≤ 2 |
| Wear group | NF 189 | group | T |
| Type binder content | EN ISO 10582 | type | I |
| Dimensional stability | EN ISO 23999 (EN 434) | % | ≤ 0.40 |
| Residual indentation (requirement) | EN ISO 24343-1 (EN 433) | mm | ≤ 0.10 |
| Residual indentation (average measure) | | mm | ~ 0.03 |
| Castor chair test (type W) | ISO 4918 (EN 425) | - | OK |
| Thermal conductivity | EN ISO 10456 (EN 12 524) | W/(m.K) | 0.25 |
| Colour fastness | EN 20 105 - B02 | degré | ≥ 6 |
| Chemical products resistance | EN ISO 26987 (EN 423) | - | OK |
| Anti-bacterial activity (MRSA) (1) | ISO 22196 | - | > 99% Inhibits growth |

ENVIRONMENT / INDOOR AIR QUALITY

| | | | |
|--------------------|-------------|--------------------|-------------|
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 100 |
| Certification | - | - | Floorscore® |

CE MARKING

| | | | |
|--|----------|---|---|
|  | EN 14041 | - |    |
| | | - |  |

(1) The implementation of an effective cleaning regime is the best defence against infection