

Technical data sheet
Technical data

FINETT DIMENSION

| Wear layer | 100 % polyamide dorix [®] | | | | | | | | | | | | | | |
|---|---|----------|------|------|------|------|------|------|------------|------|------|------|------|------|------|
| Back | Textile backing (non-woven fabric) | | | | | | | | | | | | | | |
| Emission tested acc. to CRI-principles | GREEN LABEL PLUS GLP100090 | | | | | | | | | | | | | | |
| Health safety Environmental label RAL-UZ 128 | BLUE ANGEL Contract No. 30258 | | | | | | | | | | | | | | |
| DGNB criterion ENV 1.2 | Quality Level 4 (QL 4) | | | | | | | | | | | | | | |
| REACH regulation No. 1907/2006 article 33 | does not contain any substances mentioned in the SVHC list | | | | | | | | | | | | | | |
| Total weight ISO 8543 | 1600 g/m ² | | | | | | | | | | | | | | |
| Fibre weight | 650 g/m ² | | | | | | | | | | | | | | |
| Wear layer weight EN 984 | 600 g/m ² | | | | | | | | | | | | | | |
| Total thickness ISO 1765 | 6,2 mm | | | | | | | | | | | | | | |
| Dimensions | Plank 25 x 100 cm 4 m ² /carton Tile 50 x 50 cm 4 m ² /carton | | | | | | | | | | | | | | |
| Level of use EN 1307 | class 33 heavy duty | | | | | | | | | | | | | | |
| Colour fastness to light ISO 105-B02 | 7 | | | | | | | | | | | | | | |
| Fire rating EN 13501-1 | B _{fl} -s1 | | | | | | | | | | | | | | |
| Slipperiness EN 13893 | DS (> 0,30) | | | | | | | | | | | | | | |
| Thermal resistance ISO 8302 | 0,10 m ² K/W suitable for underfloor heating | | | | | | | | | | | | | | |
| Impact sound insulation ISO 10140 | 23 dB | | | | | | | | | | | | | | |
| Level of sound absorption ISO 354 | <table border="1"> <thead> <tr> <th>Freq. Hz</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>α_s</td> <td>0,05</td> <td>0,05</td> <td>0,10</td> <td>0,18</td> <td>0,42</td> <td>0,69</td> </tr> </tbody> </table> | Freq. Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 | α_s | 0,05 | 0,05 | 0,10 | 0,18 | 0,42 | 0,69 |
| Freq. Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 | | | | | | | | | |
| α_s | 0,05 | 0,05 | 0,10 | 0,18 | 0,42 | 0,69 | | | | | | | | | |
| Anti-static ISO 6356 | ≤ 2,0 kV | | | | | | | | | | | | | | |
| Special colours | > 1000 m ² | | | | | | | | | | | | | | |
| Installation DIN 18365 | Removeable installation with a suitable tackifier or dry adhesive. See installation instruction Modules. | | | | | | | | | | | | | | |



We always recommend to order larger samples. Subject to product improvements and usual colour deviations, also possible between tiles and rolls. Please also consult our installation and cleaning and maintenance instructions.

Traditional needled carpets consist of a mixture of coloured coarse fibers, which give the finished product the typical mottled look. The range of FINDEISEN also includes numerous plain colours in coarse and fine fiber optics. This results in particularly elegant surface textures with a partially felt-like appearance and a soft feel.

As with other materials, the same applies to needled carpets: covered and mottled colours hide possible stains better than bright and colourful uni shades. By choosing less sensitive colour combinations, the necessary cleaning intervals* can be extended accordingly.

FINETT needled carpets are manufactured with utmost care and according to the latest state of the art in Ettlingen/Germany. Minor optical irregularities in the appearance of the product (for example non-matching fibers) as well as colour deviations in the sense of chapter 2.8 of the current commentary on DIN 18365 can not always be avoided due to the production process and are not a defect**.

* See also our cleaning and care instructions or the current commentary to DIN 18365: "Precondition for the suitability of the floor covering is a cleaning and care (value retention) tailored to the load, sufficient clean-up zones and the usage-relevant consideration of the colour scheme."
** The obligations of the processor according to § 377 HGB remain unaffected.



www.blauer-engel.de/uz128



Member of the

