




DESCRIPTION			
Total thickness	EN ISO 24346 (EN 428)	mm	2.00
	ASTM F386-02	inch	0.08
Wearlayer thickness	EN ISO 24340 (EN 429)	mm	0.70
	ASTM F410-02	inch	0.028
Weight	EN ISO 23997 (EN 430)	g/sq.m	2635
Width of sheet	EN ISO 24341 (EN 426)	cm	200
	-	feet - inch	6'6"
Length of sheet	EN ISO 24341 (EN 426)	lm	25
	-	feet - inch	82'
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil (1)	DIN 51130	class	R10
PERFORMANCE			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	NF 189	group	T
Type binder content	ISO 10582	Type	I
Dimensional stability	EN ISO 23999 (EN 434)	%	≤0.40
Residual indentation (requirement)	EN ISO 24343-1 (EN 433)	mm	≤ 0.10
Residual indentation (average value measured)	-	mm	ca. 0.03
Impact sound insulation	EN ISO 717-2	dB	6
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥6
Surface treatment	-	-	Protecsol®
Chemical products resistance	EN ISO 26987 (EN 423)	-	OK
Anti-bacterial activity (E. coli - S. aureus – MRSA) (2)	ISO 22196	-	> 99 % Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	
		-	

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges

(2) The implementation of an effective cleaning regime is the best defence against infection