



*Reduce Your Risk!®*

**Independent Slip Testing Services**

GLOBAL PRODUCT CLASSIFICATION

# TEST REPORT

## SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS AS 4586-2013

### Appendix A - Wet Pendulum Testing

*Prepared For:*

**Advance Flooring Company**

*Product Description:*

**Axis**

*Test Date:*

**23/05/2015**



# Independent Slip Testing Services

+61 (0) 411 600 733 www.slip-testing.com.au | +64 (0) 279 735 266 www.slip-testing.co.nz  
 +65 9390 2188 www.slip-testingsingapore.com

**Report Prepared for:**

Advance Flooring Company  
 PO Box 13184  
 Auckland 1643 New Zealand

Page #: 1 of 1  
 Program #: 2008

**Test Date:**

23/05/2015

**Test Site:**

Independent Slip Testing Services- Three Kings New Zealand

**Testing Technician:**

M. Walton

**Testing Instrument:**

Mastrad Wet Pendulum Skid Tester with 4S rubber slider  
 Testing Instrument Serial #: SK1225 (W2)

## TESTING SPECIMENS DESCRIPTION, SIZE &amp; COATING (If applicable)

1. 1 x Axis, Black Carpet on Plastic Backing, 30x30cm
2. 1 x Axis, Black Carpet on Plastic Backing, 30x30cm
3. 1 x Axis, Black Carpet on Plastic Backing, 30x30cm
4. 1 x Axis, Black Carpet on Plastic Backing, 30x30cm
5. 1 x Axis, Black Carpet on Plastic Backing, 30x30cm

**Surface Condition:**

Textured

**Cleaning:**

Tested as received

**Fixed/ Unfixed:**

Unfixed

**Rz Mean:**

n/a

**Environmental Conditions:**

Internal- Non Airconditioned

**Air Temp:**

20 Deg.C

**Direction of Test:**

As indicated on underside of sample

**Slope:**

n/a

**AS 4586-2013**

## INTERPRETATION OF THE WET PENDULUM RESULTS

Classification	Pendulum mean BPN (4S rubber)
P5	>54
P4	45-54
P3	35-44
P2	25-34
P1	12-24
P0	<12

**TEST RESULTS**

Specimen	#1 Result:	49 BPN	Slider condition (P400):	84 BPN
	#2 Result:	55 BPN	Slider condition (Lapping):	62 BPN
	#3 Result:	53 BPN	Temperature adjustment:	n/a
	#4 Result:	54 BPN		
	#5 Result:	53 BPN		

**CLASSIFICATION**

CLASSIFICATION	PENDULUM MEAN BPN (4S rubber)
<b>P4</b>	<b>53</b>

The mean results of the five specimens is reported (rounded to nearest whole number)

^ An individual result both below the result classification and below the mean result minus 20% shall be considered of lower classification

Maximum Slope Design Value (when dry):	4.5 deg.
Maximum Slope Design Value (when wet):	4 deg.

^NCC Code provides reference for ramps up to 1:8

**DISCLAIMER:**

ISTS accepts no civil liability or responsibility for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. The test report is intended for viewing purposes solely for the named recipient identified above. The slip test report remains the property of ISTS. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.

Accredited for compliance with ISO/IEC 17025. NATA is a signatory to the APLAC mutual recognition arrangement for the mutual recognition of the equivalence of testing, calibration and inspection reports

NATA Accreditation #14967

Signatory: Mick Walton



Testing was carried out using the Wet Pendulum Test Method (using 4S rubber slider)  
 in accordance with Australian Standard AS 4586-2013 Appendix A.

## WET TEST RESULTS INTERPRETATION GUIDE- NATIONAL CONSTRUCTION CODE (AUS)

### INTERPRETING WET TEST RESULTS

- Step 1** Compare description of reported test location to the most relevant location description in Table 3A. Note the pendulum classification for that location.
- Step 2** Note the pendulum classification BPN range in Table 2.
- Step 3** Compare the BPN range and classification to the actual test result.

### NATIONAL CONSTRUCTION CODE COMPLIANCE CLASSIFICATIONS

**\* TABLE 3A**

Minimum wet pendulum test or oil-wet inclining platform classifications that are deemed to satisfy the building applications in the National Construction Code

Location	Wet pendulum test	Oil-wet inclining platform test
<b>Stair Treads and Stairway Landings in Buildings Covered by NCC Volumes One and Two</b>		
Stair treads and a stairway landing (when dry)	P3	R10
Stair treads and a stairway landing (when wet)	P4	R11
<b>Nosings for Stair Treads and Stairway Landings in Buildings Covered by NCC Volumes One and Two</b>		
Dry stair tread, a stair non-skid nosing strip and a stairway landing	P3	
Wet stair tread, a stair non-skid nosing strip and a stairway landing	P4	
<b>Ramps in Buildings Covered by NCC Volumes One and Two</b>		
Ramps not steeper than 1:14 gradient (when dry)	P3	R10
Ramps not steeper than 1:14 gradient (when wet)	P4	R11
Ramps steeper than 1:14 up but not steeper than 1:8 (when dry)	P4	R11
Ramps steeper than 1:14 up but not steeper than 1:8 (when wet)	P5	R12

NOTE: NCC compliance is demonstrated by achieving the values set out in this Table for either the wet pendulum test or the oil-wet inclining ramp test. It is not necessary to meet both criteria.

**\*TABLE 2**

Classification of Pedestrian Surface Materials according to the AS 4586-2013 wet pendulum test

Pendulum* mean BPN		Classification	Previously stated as (HB197:1999)
Four S rubber	TRL rubber		
>54	>44	P5	V
45-54	40-44	P4	W
35-44	35-39	P3	X
25-34	20-34	P2	Y
12-24	< 20	P1	Z
<12	-	P0	Z

### TREATMENT OPTIONS

For test results that achieve a BPN result below the NCC requirements the following are options are available to increase slip resistance and reduce your risk

As a guide, possible styles of treatments we see our clients using to improve slip resistance include:

<b>Cleaning procedures</b>	Detergent residues can build up over time with heavy detergent use.
<b>Acid etching</b>	For tiled surfaces. Can vary in performance with different tile types.
<b>Wet sand / Soda blasting</b>	To obtain a textured finish to tiles and other hard surfaces (may require sealing).
<b>Shot blasting</b>	More extreme treatment to wet sand blasting (may require sealing).
<b>Textured coatings</b>	Ensure a consistent texture is achieved.
<b>Surface replacement</b>	Replacement surface may be the most cost effective option in some locations.

*For treatment suppliers in your local area search the internet for options listed above or in the yellow pages 'flooring treatments' section. ISTS recommends sourcing a number of detailed proposals when considering treatments, outlining expected slip resistance improvements, visual changes, clean ability and life expectancy.*

### ADDITIONAL NOTES & REFERENCES

**'R' Ratings** The Ramp 'R' ratings are obtained using the ramp test. An 'R' rating can not be achieved for in-situ testing. There is no correlation between 'R' ratings and wet pendulum test results.

**References** \*Table 3A- HB198:2014 "Guide to the specification and testing of slip resistance of pedestrian surfaces" Standards Australia Limited 2014.

\*Table 2- AS 4586-2013 "Slip resistance classification of new pedestrian surface materials".

*\*The information provided is intended as a guide only, consult the referenced publications for further information in regards to measurement results and recommendations.*



Reduce Your Risk!<sup>®</sup>  
**Independent Slip Testing Services**  
GLOBAL PRODUCT CLASSIFICATION

# Independent Slip Testing Services

+61 (0) 411 600 733 www.sliptesting.com.au | +64 (0) 279 735 266 www.sliptesting.co.nz | +65 9390 2188 www.sliptestingsingapore.com

## WET TEST RESULTS INTERPRETATION GUIDE- PARTICULAR APPLICATIONS...NON NCC (AUS)

### INTERPRETING WET TEST RESULTS

- Step 1** Compare description of reported test location to the most relevant location description in Table 3B. Note the pendulum classification for that location.
- Step 2** Note the pendulum classification BPN range in Table 2.
- Step 3** Compare the BPN range and classification to the actual test result.

### NATIONAL CONSTRUCTION CODE COMPLIANCE CLASSIFICATIONS

**\* TABLE 3B**

Wet pendulum test or oil-wet inclining platform classifications for applications where the NCC does not require slip resistance

Location	Wet pendulum test	Oil-wet inclining platform test
<b>External Pavements and Ramps</b>		
External ramps including sloping driveways, footpaths etc. steeper than 1 in 14	P5	R12
External ramps including sloping driveways, footpaths, etc., under 1:14, external sales areas (eg. markets), external carpark areas, external colonnades, walkways, pedestrian crossings, balconies, verandas, carports, driveways, courtyards and roof decks	P4	R11
Undercover car parks	P3	R10
<b>Hotels, Offices, Public Buildings, Schools and Kindergartens</b>		
Entries and access areas including hotels, offices, public buildings, schools, kindergartens, common areas of public buildings, internal lift lobbies		
Wet area	P3	R10
Transitional area	P2	R9
Dry area	P1 (see Note 3)	R9
Toilet facilities in offices, hotels and shopping centres	P3	R10
Hotel apartment bathrooms, ensuites and toilets	P2	A
Hotel apartment kitchens and laundries	P2	R9
<b>Loading Docks, Commercial Kitchens, Cold Stores, Serving Areas</b>		
Loading docks under cover and commercial kitchens	P5	R12
Serving areas behind bars in public hotels and clubs, cold stores and freezers	P4	R11

### Supermarkets and Shopping Centres

Fast food outlets, buffet food servery areas, food courts and fast food dining areas in shopping centres

P3

R10

Shop and supermarket fresh fruit and vegetable areas

P3

R10

Shop entry areas with external entrances

P3

R10

Supermarket aisles (except fresh food areas)

P1 (see Note 3)

R9

Other separate shops inside shopping centres - wet

P3

R10

Other separate shops inside shopping centres - dry

P1 (see Note 3)

R9

### Swimming Pools and Sporting Facilities

Swimming pool ramps and stairs leading to water

P5

C

Swimming pool surrounds and communal shower rooms

P4

B

Communal changing rooms

P3

A

Undercover concourse areas of sports stadiums

P3

R10

### Hospitals and Aged Care Facilities

Bathrooms and en suites in hospitals and aged care facilities

P3

B

Wards and corridors in hospital and aged care facilities

P2

R9

**\*TABLE 2**

Classification of Pedestrian Surface Materials according to the  
AS 4586-2013 wet pendulum test

Pendulum* mean BPN		Classification	Previously stated as (HB197:1999)
Four S rubber	TRL rubber		
>54	>44	P5	V
45-54	40-44	P4	W
35-44	35-39	P3	X
25-34	20-34	P2	Y
12-24	< 20	P1	Z
<12	-	P0	Z

### ADDITIONAL NOTES & REFERENCES

- 'R' Ratings** The Ramp 'R' ratings are obtained using the ramp test. An 'R' rating can not be achieved for in-situ testing. There is no correlation between 'R' ratings and wet pendulum test results.
- References** \*Table 3B- HB198:2014 "Guide to the specification and testing of slip resistance of pedestrian surfaces" Standards Australia Limited 2014.
- \*Table 2- AS 4586-2013 "Slip resistance classification of new pedestrian surface materials".
- \*The information provided is intended as a guide only, consult the referenced publications for further information.*



*Reduce Your Risk!®*

**Independent Slip Testing Services**

GLOBAL PRODUCT CLASSIFICATION

## TEST PRODUCT IMAGE

**Product Description:** Axis

**Test Date:** 23/05/2015

