

Rinos BV  
Klaas Fuitestraat 12  
8280 AA Genemuiden  
NETHERLANDS

Eurofins Product Testing A/S  
Smedeskovvej 38  
8464 Galten  
Denmark

CustomerSupport@eurofins.com  
www.eurofins.com/VOC-testing

## VOC EMISSION TEST REPORT


### Indoor Air Comfort GOLD®

18 February 2022

## 1 Sample Information

Sample name	Duratap Naturel 23mm
Batch no.	X66
Stated production date	20/12/2021
Product type	Textile flooring
Sample reception	28/12/2021

## 2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
French VOC Regulation		Decree of March 2011 (DEVL1101903D) and Arrêté of April 2011 (DEVL1104875A) modified in February 2012 (DEVL1133129A)
French CMR components	Pass	Regulation of April and May 2009 (DEVP0908633A and DEVP0910046A)
Italian CAM Edilizia	Pass	Decree 11 October 2017 (GU n.259 del 6-11-2017)
ABG/AgBB	Fail	Ausschuss zur gesundheitlichen Bewertung von Bauprodukten (June 2021)
Belgian Regulation	Fail	Royal decree of May 2014 (C-2014/24239)
Indoor Air Comfort®	Fail	Indoor Air Comfort 7.0 of May 2020
Indoor Air Comfort GOLD®	Fail	Indoor Air Comfort GOLD 7.0 of May 2020
Formaldehyde Emission Class <sup>s</sup>	E1	EN 16516 - July 2020, EN14041:2018
BREEAM International	Fail	BREEAM International New Construction v2.0 (2016)
LEED v4.1 BETA (outside U.S.)	Fail	LEED v4.1 BETA for Building Design and Construction (February 2021)
BREEAM® NOR	Fail	BREEAM-NOR New Construction v1.2 (2019)

Full details based on the testing and direct comparison with limit values are available in the following pages  
Regarding pass/fail decision rule please see appendix

  
Rasmus Stengaard Christensen  
Analytical Service Manager, MSc in Chemistry

## Table of contents

<b>1</b>	<b>Sample Information</b>	<b>1</b>
<b>2</b>	<b>Brief Evaluation of the Results</b>	<b>1</b>
<b>3</b>	<b>Applied Test Methods</b>	<b>3</b>
3.1	General Test References	3
3.2	Specific Laboratory Sampling and Analyses	3
<b>4</b>	<b>Test Parameters, Sample Preparation and Deviations</b>	<b>4</b>
4.1	VOC Emission Chamber Test Parameters	4
4.2	Preparation of the Test Specimen	4
4.3	Picture of Sample	4
4.4	Deviations from Referenced Protocols and Regulations	4
<b>5</b>	<b>Results</b>	<b>5</b>
5.1	VOC Emission Test Results after 3 Days	5
5.2	VOC Emission Test Results after 28 Days	7
<b>6</b>	<b>Summary and Evaluation of the Results</b>	<b>9</b>
6.1	Comparison with Limit Values of the French VOC Regulation	9
6.2	Comparison with Limit Values of the CMR Components	9
6.3	Comparison with Limit Values of the Italian CAM Regulation	10
6.4	Formaldehyde Emission Class <sup>s</sup>	10
6.5	Comparison with Limit Values of AgBB/ABG	11
6.6	Comparison with Limit Values of the Belgian Regulation	11
6.7	Comparison with Limit Values of LEED v4.1 BETA	11
6.8	Comparison with Limit Values of BREEAM <sup>®</sup> NOR	12
6.9	Comparison with Limit Values of BREEAM International	12
6.10	Comparison with Limit Values of Indoor Air Comfort <sup>®</sup>	12
6.11	Comparison with Limit Values of Indoor Air Comfort Gold <sup>®</sup>	13
<b>7</b>	<b>Appendices</b>	<b>14</b>
7.1	Chromatogram of VOC Emissions after 3 Days	14
7.2	Chromatogram of VOC Emissions after 28 Days	14
7.3	How to Understand the Results	15
7.4	Applied LCI and NIK Values	16
7.5	Description of VOC Emission Test	17
7.6	Quality Assurance	19
7.7	Accreditation	19
7.8	Uncertainty of the Test Method	19
7.9	Decision Rules	19
7.10	Version History	19

### 3 Applied Test Methods

#### 3.1 General Test References

Regulation, protocol or standard	Version	Reporting limit VOC [ $\mu\text{g}/\text{m}^3$ ]	Calculation of TVOC	Combined uncertainty <sup>a</sup> [RSD(%)]
EN 16516	2017 + A1:2020	5	Toluene equivalents	22%
ISO 16000 -3 -6 -9 -11	2006-2021 depending on part	2	Toluene equivalents	22%
ASTM D5116-10	2010	-	-	-
Specifications Indoor Air Comfort Gold	7.0 of May 2020	5	Toluene equivalents	22%
French VOC Classes	Decree of 03/2011 (DEVL1101903D) and arrêté of 02/2012 (DEVL1133129A)	2	Toluene equivalents	22%
Italian CAM Edilizia	Decree 11 October 2017. Section 2.3.5.5	2	Toluene equivalents	22%
AgBB (MVV TB/ABG)	June 2021 (2020/2019)	5	Compound Specific	22%
Belgian VOC	Royal decree of May 2014 (C - 2014 / 24239)	5	Toluene equivalents	22%
BREEAM® NOR	BREEAM-NOR New Construction v1.2 (2019)	5	Toluene equivalents	22%
BREEAM International	BREEAM International New Construction v2.0 (2016)	5	Toluene equivalents	22%
LEED v4.1 BETA (outside U.S.)	February 2021	5	Compound Specific	22%

#### 3.2 Specific Laboratory Sampling and Analyses

Procedure	External Method	Internal SOP	Quantification limit / sampling volume	Analytical principle	Uncertainty <sup>a</sup> [RSD(%)]
Sample preparation	ISO 16000-11:2006, EN 16516:2017+A1:2020, AgBB:2021, EMICODE:2020	71M549810	-	-	-
Emission chamber testing	ISO 16000-9:2006, EN 16516:2017+A1:2020	71M549811	-	Chamber and air control	-
Sampling of VOC	ISO 16000-6:2021, EN 16516:2017+A1:2020	71M549812	5 L	Tenax TA	-
Analysis of VOC	ISO 16000-6:2021, EN 16516:2017+A1:2020	71M542808B	1 $\mu\text{g}/\text{m}^3$	ATD-GC/MS	10%
Sampling of aldehydes	ISO 16000-3:2011, EN 16516:2017+A1:2020	71M549812	35 L	DNPH	-
Analysis of aldehydes	ISO 16000-3:2011, EN 16516:2017+A1:2020	71M548400	3-6 $\mu\text{g}/\text{m}^3$	HPLC-UV	10%
Sampling of phthalates*	ISO 16000-33:2017, MEL-09:2003	71M549812	60 L	XAD-2	-
Analysis of phthalates*	ISO 16000-33:2017	71M546060	0.6 $\mu\text{g}/\text{m}^3$	GC/MS	10%

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

## 4 Test Parameters, Sample Preparation and Deviations


### 4.1 VOC Emission Chamber Test Parameters

Parameter	Value	Parameter	Value
Chamber volume, V[L]	119	Preconditioning period	-
Air Change rate, n[h <sup>-1</sup> ]	0.5	Chamber test period	13/01/2022 - 10/02/2022
Area specific ventilation rate, q [m/h or m <sup>3</sup> /m <sup>2</sup> /h]	1.25	Analytical test period	13/01/2022 - 16/02/2022
Relative humidity of supply air, RH [%]	50 ± 3	Loading factor [m <sup>2</sup> /m <sup>3</sup> ]	0.4
Temperature of supply air, T [°C]	23 ± 1	Test scenario	Flooring or ceiling

### 4.2 Preparation of the Test Specimen

Edges and back were covered with aluminium foil and the sample was mounted into a frame in accordance with JIS A 1901.

### 4.3 Picture of Sample



### 4.4 Deviations from Referenced Protocols and Regulations

No deviations from the referenced test methods were observed except the general deviations.

#### 4.4.1 General Deviations

Formaldehyde emission class is tested according to EN 16516 as specified in EN 14041:2018, which was not yet published in the EU journal and as a consequence not yet valid for CE labelling of resilient and textile flooring. The referenced conclusion is consequently only for advisory use.

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

## 5 Results

### 5.1 VOC Emission Test Results after 3 Days

	CAS No.	Retention time [min]	ID-Cat	Specific Conc. [µg/m <sup>3</sup> ]	Toluene eq. [µg/m <sup>3</sup> ]	Specific SER [µg/(m <sup>2</sup> ·h)]	R <sub>D</sub>	R <sub>B</sub>
<b>VOC with NIK/LCI</b>								
Acetic acid * a	64-19-7	1.98	1	48	5.4	60	0.040	0.040
Hexanal	66-25-1	4.92	1	16	7.9	20	0.018	0.018
2-Methylnonane *	871-83-0	8.09	1	6.3	6.5	7.9	0.0011	0.0011
n-Decane	124-18-5	8.64	1	110	110	140	0.019	0.019
4-Methyldecane *	2847-72-5	8.98	1	94	94	120	0.016	0.016
2-Ethyl-1-hexanol	104-76-7	9.10	1	1200	850	1500	3.9	3.9
n-Undecane	1120-21-4	10.03	1	290	270	370	0.049	0.049
4-Methylundecane *	2980-69-0	10.76	2	61	61	76	0.010	0.010
n-Dodecane	112-40-3	11.23	1	140	160	170	0.023	0.023
2,6-Dimethylundecane *	17301-23-4	11.39	2	72	72	90	0.012	0.012
n-Tridecane	629-50-5	12.30	1	7.9	9.3	9.9	0.0013	0.0013
Saturated aliphatic hydrocarbons higher than C9 *		7.4-12.6	2	2400	2400	3000	0.40	0.40
<b>VOC without NIK/LCI</b>								
5-Methyldecane *	13151-35-4	9.47	2	31	31	39		
3-Methyldecane *	13151-34-3	9.65	2	65	65	82		
2-Methylundecane *	7045-71-8	10.81	2	89	89	110		
1-Chlorododecane *	112-52-7	14.01	2	12	12	16		
<b>Sum of VOC without NIK/LCI</b>				200	200	250		
<b>VVOC compounds</b>								
None determined								
<b>TVOC</b>								
				< 5	< 5	< 7		
<b>SVOC compounds</b>								
None determined								
<b>TSVOC</b>								
				< 5	< 5	< 7		
<b>Carcinogens</b>								
<b>Total carcinogens</b>								
				< 1	< 1	< 2		
<b>Aldehydes</b>								
Formaldehyde	50-00-0		1	< 3		< 4		
Acetaldehyde	75-07-0		1	3.9		4.9		

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

	CAS No.	Retention time [min]	ID-Cat	Specific Conc. [µg/m <sup>3</sup> ]	Toluene eq. [µg/m <sup>3</sup> ]	Specific SER [µg/(m <sup>2</sup> ·h)]	R <sub>D</sub>	R <sub>B</sub>
Propionaldehyde	123-38-6		1	< 3		< 4		
Butyraldehyde	123-72-8		1	< 3		< 4		
Acrolein *	107-02-8		1	< 5		< 7		
2-Butenal *	123-73-9		1	< 5		< 7		
Glutaraldehyde *	111-30-8		1	< 5		< 7		
Octanal *	124-13-0		1	< 5		< 7		
Nonanal *	124-19-6		1	< 5		< 7		
Decanal *	112-31-2		1	< 5		< 7		
<b>R-values</b>							4.5	4.5
<b>TVOC</b>				4600	4200	5800		

## 5.2 VOC Emission Test Results after 28 Days

	CAS No.	Retention time [min]	ID-Cat	Specific Conc. [µg/m <sup>3</sup> ]	Toluene eq. [µg/m <sup>3</sup> ]	Specific SER [µg/(m <sup>2</sup> ·h)]	R <sub>D</sub>	R <sub>B</sub>
<b>VOC with NIK/LCI</b>								
Acetic acid * a	64-19-7	1.99	1	84	9.4	100	0.070	0.070
Hexanal	66-25-1	4.91	1	7.4	< 5	9.3	0.0082	0.0082
2-Ethyl-1-hexanol	104-76-7	9.09	1	620	450	770	2.1	2.1
n-Undecane	1120-21-4	10.04	1	67	62	84	0.011	0.011
n-Dodecane	112-40-3	11.24	1	66	74	82	0.011	0.011
n-Tridecane	629-50-5	12.32	1	5.4	6.4	6.8	0.0009	0.0009
Saturated aliphatic hydrocarbons higher than C <sub>9</sub> *		7.9-12.2	2	720	720	900	0.12	0.12
<b>VOC without NIK/LCI</b>								
1-Chlorododecane *	112-52-7	14.03	3	12	12	14		
<b>Sum of VOC without NIK/LCI</b>				12	12	14		
<b>VVOC compounds</b>								
None determined								
<b>TVVOC</b>								
				< 5	< 5	< 7		
<b>SVOC compounds</b>								
None determined								
<b>TSVOC</b>								
				< 5	< 5	< 7		
<b>Carcinogens</b>								
<b>Total carcinogens</b>								
				< 1	< 1	< 2		
<b>CMR (French reg.)</b>								
Benzene	71-43-2		1	< 1		< 2		
Trichloroethylene	79-01-6		1	< 1		< 2		
Dibutylphthalate (DBP)*	84-74-2		1	< 1		< 2		
Diethylhexylphthalate (DEHP)*	117-81-7		1	< 1		< 2		
<b>Other phthalates</b>								
Dimethylphthalate (DMP)*	131-11-3		1	< 1		< 2		
Diethylphthalate (DEP)*	84-66-2		1	< 1		< 2		
Benzylbutylphthalate (BBP)*	85-68-7		1	< 1		< 2		
Dioctylphthalate (DOP)*	117-84-0		1	< 1		< 2		

The results are only valid for the tested sample(s).





This report may only be copied or reprinted in its entity.

	CAS No.	Retention time [min]	ID-Cat	Specific Conc. [µg/m <sup>3</sup> ]	Toluene eq. [µg/m <sup>3</sup> ]	Specific SER [µg/(m <sup>2</sup> ·h)]	R <sub>D</sub>	R <sub>B</sub>
<b>Aldehydes</b>								
Formaldehyde	50-00-0		1	< 3		< 4		
Acetaldehyde	75-07-0		1	< 3		< 4		
Propionaldehyde	123-38-6		1	< 3		< 4		
Butyraldehyde	123-72-8		1	< 3		< 4		
Acrolein *	107-02-8		1	< 5		< 7		
2-Butenal *	123-73-9		1	< 5		< 7		
Glutaraldehyde *	111-30-8		1	< 5		< 7		
Octanal *	124-13-0		1	< 5		< 7		
Nonanal *	124-19-6		1	< 5		< 7		
Decanal *	112-31-2		1	< 5		< 7		
<b>R-values</b>							2.3	2.3
<b>TVOC</b>				1600	1300	2000		
TVOC (French label)					1300			
Toluene	108-88-3			< 2	< 2	< 3		
Tetrachloroethylene	127-18-4			< 2	< 2	< 3		
Ethylbenzene	100-41-4			< 2	< 2	< 3		
Xylene	1330-20-7			< 2	< 2	< 3		
Styrene	100-42-5			< 2	< 2	< 3		
2-Butoxyethanol	111-76-2			< 2	< 2	< 3		
1,2,4-Trimethylbenzene	95-63-6			< 2	< 2	< 3		
1,4-Dichlorobenzene	106-46-7			< 2	< 2	< 3		



## 6 Summary and Evaluation of the Results

### 6.1 Comparison with Limit Values of the French VOC Regulation

	CAS No.	Conc. 28 days $\mu\text{g}/\text{m}^3$	 $\mu\text{g}/\text{m}^3$	 $\mu\text{g}/\text{m}^3$	 $\mu\text{g}/\text{m}^3$	 $\mu\text{g}/\text{m}^3$
TVOC	-	1300	> 2000	< 2000	< 1500	< 1000
Formaldehyde	50-00-0	< 3	> 120	< 120	< 60	< 10
Acetaldehyde	75-07-0	< 3	> 400	< 400	< 300	< 200
Toluene	108-88-3	< 2	> 600	< 600	< 450	< 300
Tetrachloroethylene	127-18-4	< 2	> 500	< 500	< 350	< 250
Ethylbenzene	100-41-4	< 2	> 1500	< 1500	< 1000	< 750
Xylene	1330-20-7	< 2	> 400	< 400	< 300	< 200
Styrene	100-42-5	< 2	> 500	< 500	< 350	< 250
2-Butoxyethanol	111-76-2	< 2	> 2000	< 2000	< 1500	< 1000
1,2,4-Trimethylbenzene	95-63-6	< 2	> 2000	< 2000	< 1500	< 1000
1,4-Dichlorobenzene	106-46-7	< 2	> 120	< 120	< 90	< 60

The product was assigned a VOC emission class without taking into account the measurement uncertainty associated with the result. As specified in French Decree no. 2011-321 of March 23 2011, correct assignment of the VOC emission class is the sole responsibility of the party responsible for distribution of the product in the French market.

### 6.2 Comparison with Limit Values of the CMR Components

CMR (French reg.)	CAS No.	Conc. 28 days $\mu\text{g}/\text{m}^3$	Max. allowed air concentration $\mu\text{g}/\text{m}^3$
Benzene	71-43-2	< 1	< 1
Trichloroethylene	79-01-6	< 1	< 1
Dibutylphthalate (DBP)*	84-74-2	< 1	< 1
Diethylhexylphthalate (DEHP)*	117-81-7	< 1	< 1

### 6.3 Comparison with Limit Values of the Italian CAM Regulation

	CAS No.	Conc. 28 days $\mu\text{g}/\text{m}^3$	Limit value 28 days $\mu\text{g}/\text{m}^3$
TVOC	-	1300	< 1500
Formaldehyde	50-00-0	< 3	< 60
Acetaldehyde	75-07-0	< 3	< 300
Toluene	108-88-3	< 2	< 450
Tetrachloroethylene	127-18-4	< 2	< 350
Ethylbenzene	100-41-4	< 2	< 1000
Xylene	1330-20-7	< 2	< 300
Styrene	100-42-5	< 2	< 350
2-Butoxyethanol	111-76-2	< 2	< 1500
1,2,4-Trimethylbenzene	95-63-6	< 2	< 1500
1,4-Dichlorobenzene	106-46-7	< 2	< 90
Benzene	71-43-2	< 1	< 1
Trichloroethylene	79-01-6	< 1	< 1
Dibutylphthalate (DBP)*	84-74-2	< 1	< 1
Diethylhexylphthalate (DEHP)*	117-81-7	< 1	< 1

The product was assigned a VOC emission class without taking into account the measurement uncertainty associated with the result.

### 6.4 Formaldehyde Emission Class<sup>s</sup>

Parameter	Concentration $\text{mg}/\text{m}^3$	E2 $\text{mg}/\text{m}^3$	E1 $\text{mg}/\text{m}^3$
<b>Formaldehyde 28 days</b>	< 0.003	> 0.124	≤ 0.124

The formaldehyde result is based on chamber testing and DNPH sampling according to ISO 16000/EN 16516.

## 6.5 Comparison with Limit Values of AgBB/ABG

Parameter	Test after 3 days		Test after 28 days	
	Concentration mg/m <sup>3</sup>	Limit Value mg/m <sup>3</sup>	Concentration mg/m <sup>3</sup>	Limit Value mg/m <sup>3</sup>
TVOC	4.6	≤ 10	1.6	≤ 1.0
TSVOC	< 0.005	-	< 0.005	≤ 0.1
R-value (dimensionless)	4.5	-	2.3	≤ 1
Sum of VOC without NIK/LCI	0.20	-	0.012	≤ 0.1
Formaldehyde	-	-	< 0.003	≤ 0.1
Total carcinogens	< 0.001	≤ 0.01	< 0.001	≤ 0.001

Compliance with the limits alone does not replace an approval or voluntary documentation by a Technical Assessment Body according to the Construction Product Regulation. This requires an application and approval. See [www.eurofins.com/dibt-procedures](http://www.eurofins.com/dibt-procedures).

## 6.6 Comparison with Limit Values of the Belgian Regulation

Parameter	Test after 28 days	
	Concentration µg/m <sup>3</sup>	Limit Value µg/m <sup>3</sup>
TVOC (EN 16516)	1300	≤ 1000
TSVOC	< 5	≤ 100
R-value (dimensionless)	2.3	≤ 1
Total carcinogens	< 1	≤ 1
Toluene	< 5	≤ 300
Formaldehyde	< 3	≤ 100
Acetaldehyde	< 3	≤ 200

## 6.7 Comparison with Limit Values of LEED v4.1 BETA

Parameter	Test after 28 days	
	Concentration µg/m <sup>3</sup>	Limit Value µg/m <sup>3</sup>
TVOC	1600	≤ 1000
Sum of VOC without NIK/LCI	12	< 100
Formaldehyde	< 3	≤ 10
R-value (dimensionless)	2.3	≤ 1

### 6.8 Comparison with Limit Values of BREEAM® NOR

Parameter	Area specific emission rate $\mu\text{g}/(\text{m}^2\cdot\text{h})$	Limit Value $\mu\text{g}/(\text{m}^2\cdot\text{h})$
TVOC (EN 16516) 28 days	1700	$\leq 200$
Total carcinogens	$< 2$	$\leq 5$
Formaldehyde 3 days	$< 4$	$\leq 63$
Formaldehyde 28 days	$< 4$	$\leq 50$

### 6.9 Comparison with Limit Values of BREEAM International

Parameter	Concentration $\text{mg}/\text{m}^3$	Basic Level $\text{mg}/\text{m}^3$	Exemplary Level $\text{mg}/\text{m}^3$
Formaldehyde 28 days	$< 0.003$	$\leq 0.06$	$\leq 0.01$
TVOC (EN 16516) 28 days	1.3	$\leq 1.0$	$\leq 0.3$
TSVOC 28 days	$< 0.005$	-	$\leq 0.1$
total carcinogens 28 days	$< 0.001$	$\leq 0.001$	$\leq 0.001$

### 6.10 Comparison with Limit Values of Indoor Air Comfort®

	Test after 3 days		Test after 28 days	
	Concentration $\mu\text{g}/\text{m}^3$	Limit Value $\mu\text{g}/\text{m}^3$	Concentration $\mu\text{g}/\text{m}^3$	Limit Value $\mu\text{g}/\text{m}^3$
TVOC (EN 16516)	4200	$\leq 10000$	1300	$\leq 1000$
TSVOC	$< 5$	-	$< 5$	$\leq 100$
R <sub>D</sub> -value (NIK) (dimensionless)	4.5	-	2.3	$\leq 1$
R <sub>B</sub> -value (LCI) (dimensionless)	4.5	-	2.3	$\leq 1$
Sum of VOC without NIK/LCI	200	-	12	$\leq 100$
Total carcinogens	$< 1$	$\leq 10$	-	-
Any individual carcinogens	-	-	$< 1$	$\leq 1$
CMR (French reg.)	-	-	$< 1$	$\leq 1$
Formaldehyde	$< 3$	-	$< 3$	$\leq 60$
Acetaldehyde	3.9	-	$< 3$	$\leq 200$
French A+/A	-	-	Complies	

Compliance with the limits alone does not entitle to use the Indoor Air Comfort label. This requires an application, site inspection, and approval. See [www.eurofins.com/iac-procedures](http://www.eurofins.com/iac-procedures).

### 6.11 Comparison with Limit Values of Indoor Air Comfort Gold®

	Test after 3 days		Test after 28 days	
	Concentration µg/m <sup>3</sup>	Limit Value µg/m <sup>3</sup>	Concentration µg/m <sup>3</sup>	Limit Value µg/m <sup>3</sup>
<b>TVOC (EN 16516)</b>	4200	≤ 1000	1300	≤ 100
<b>TSVOC</b>	< 5	-	< 5	≤ 30
<b>R<sub>D</sub>-value (NIK) (dimensionless)</b>	4.5	-	2.3	≤ 1
<b>R<sub>B</sub>-value (LCI) (dimensionless)</b>	4.5	-	2.3	≤ 1
<b>Sum of VOC without NIK/LCI</b>	200	-	12	≤ 50
<b>Total carcinogens</b>	< 1	≤ 10	-	-
<b>Any individual carcinogens</b>	-	-	< 1	≤ 1
<b>CMR (French reg.)</b>	-	-	< 1	≤ 1
<b>Formaldehyde</b>	< 3	-	< 3	≤ 4
<b>Acetaldehyde</b>	3.9	-	< 3	≤ 4
<b>Propionaldehyde</b>	< 3	-	< 3	≤ 8
<b>Butyraldehyde</b>	< 5	-	< 5	≤ 8
<b>Octanal *</b>	< 5	-	< 5	≤ 5
<b>Nonanal *</b>	< 5	-	< 5	≤ 8
<b>Decanal *</b>	< 5	-	< 5	≤ 8
<b>4-vinylcyclohexene</b>	< 2	-	< 2	≤ 2
<b>Styrene</b>	< 2	-	< 2	≤ 2
<b>Naphthalene</b>	< 3	-	< 3	≤ 3
<b>4-phenylcyclohexene</b>	< 5	-	< 5	≤ 5
<b>Tetrachloroethylene</b>	< 5	-	< 5	≤ 10
<b>2-ethylhexanoic acid</b>	< 5	-	< 5	≤ 15
<b>Toluene</b>	< 5	-	< 5	≤ 20
<b>1,4-dichlorobenzene</b>	< 5	-	< 5	≤ 40
<b>vinylacetate</b>	< 5	-	< 5	≤ 40
<b>Xylene</b>	< 5	-	< 5	≤ 40
<b>NMP</b>	< 5	-	< 5	≤ 40
<b>Ethylbenzene</b>	< 5	-	< 5	≤ 40
<b>DBP, DEHP, DEP, BBP, DOP, DMP, each</b>	-	-	< 1	≤ 1
<b>French A+</b>	-	-	Does not comply	


Compliance with the limits alone does not entitle to use the Indoor Air Comfort GOLD label. This requires an application, site inspection, and approval. See [www.eurofins.com/iac-procedures](http://www.eurofins.com/iac-procedures).

The results are only valid for the tested sample(s).


This report may only be copied or reprinted in its entity.

## 7 Appendices

### 7.1 Chromatogram of VOC Emissions after 3 Days



### 7.2 Chromatogram of VOC Emissions after 28 Days



Please consider the different scales.

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity.

## 7.3 How to Understand the Results

### 7.3.1 Acronyms Used in the Report

<	Means less than
>	Means bigger than
*	Not a part of our accreditation
±	Please see section regarding uncertainty in the Appendices
§	Deviation from method. Please see deviation section
a	The method is not optimal for very volatile compounds. For these substances smaller results and a higher measurement uncertainty cannot be ruled out
b	The component originates from the substrate and is thus removed
c	The results have been corrected by the emission from the substrate
d	Very polar organic compounds are not suitable for reliable quantification using Tenax TA adsorbent and HP-5ms GC column. A high degree of uncertainty must be expected
e	The component may be overestimated due to contribution from the system
SER	Specific Emission Rate

### 7.3.2 Explanation of ID Category

#### Categories of Identity:

- 1: Identified by comparison with a mass spectrum obtained from library and supported by other information and quantified through specific calibration.
- 2: Identified by comparison with a mass spectrum obtained from library and supported by other information. Quantified as toluene equivalent.
- 3: Identified with a lower match by comparison with a mass spectrum obtained from a library. Quantified as toluene equivalent.
- 4: Not identified, quantified as toluene equivalent.

## 7.4 Applied LCI and NIK Values

### 7.4.1 LCI/NIK Values for Compounds found after 3 Day Measurements

Compound	CAS No.	AgBB 2021 NIK	Belgian NIK
		[µg/m <sup>3</sup> ]	[µg/m <sup>3</sup> ]
Acetic acid *	64-19-7	1200	1200
Hexanal	66-25-1	900	900
2-Methylnonane *	871-83-0	6000	6000
n-Decane	124-18-5	6000	6000
4-Methyldecane *	2847-72-5	6000	6000
2-Ethyl-1-hexanol	104-76-7	300	300
n-Undecane	1120-21-4	6000	6000
4-Methylundecane *	2980-69-0	6000	6000
n-Dodecane	112-40-3	6000	6000
2,6-Dimethylundecane *	17301-23-4	6000	6000
n-Tridecane	629-50-5	6000	6000
Saturated aliphatic hydrocarbons higher than C9 *		6000	6000
Acetaldehyde	75-07-0	300	300

### 7.4.2 LCI/NIK Values for Compounds found after 28 Day Measurements

Compound	CAS No.	AgBB 2021 NIK	Belgian NIK
		[µg/m <sup>3</sup> ]	[µg/m <sup>3</sup> ]
Acetic acid *	64-19-7	1200	1200
Hexanal	66-25-1	900	900
2-Ethyl-1-hexanol	104-76-7	300	300
n-Undecane	1120-21-4	6000	6000
n-Dodecane	112-40-3	6000	6000
n-Tridecane	629-50-5	6000	6000
Saturated aliphatic hydrocarbons higher than C9 *		6000	6000



## 7.5 Description of VOC Emission Test

### 7.5.1 Test Chamber

The test chamber is made of stainless steel. A multi-step air clean-up is performed before loading the chamber, and a blank check of the empty chamber is performed.

The chamber operation parameters are as described in the test method section. (EN 16516, ISO 16000-9, internal method no.: 71M549811).

### 7.5.2 Expression of the Test Results

All test results are calculated as specific emission rate, and as extrapolated air concentration in the European Reference Room (EN 16516, AgBB, EMICODE, M1 and Indoor Air Comfort).

### 7.5.3 Testing of Carcinogenic VOCs

The emission of carcinogens (EU Categories C1A and C1B, as per European law) is tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS (automated thermal desorption coupled with gas chromatography and mass spectroscopy using 30 m HP-5 (slightly polar) column with 0.25 mm ID and 0.25 µm film, Agilent) (EN 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All identified carcinogenic VOCs are listed; if a carcinogenic VOC is not listed then it has not been detected. Quantification is performed using the TIC signal and authentic response factors, or the relative response factors relative to toluene for the individual compounds.

This test only covers substances that can be adsorbed on Tenax TA and can be thermally desorbed. If other emissions occur, then these substances cannot be detected (or with limited reliability only).

### 7.5.4 Testing of VOC, SVOC and VVOC

The emissions of volatile organic compounds are tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS using HP-5 column (30 m, 0.25mm ID, 0.25µm film) (EN 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All single substances that are listed with a LCI/NIK value in the latest publications (hereafter referred to as target compounds) are identified if present. All other appearing VOCs are identified as far as possible. Quantification of target compounds is done using the TIC signal and authentic response factors, or the relative response factors relative to toluene. For certain compound groups, which differ significantly in chemistry from toluene, quantification is performed relative to a representative member of the group for more accurate and precise results. This can include quantification of for example glycols and acids. In addition to that, all results are also expressed in toluene equivalents. All non-target compounds, as well as all non-identified substances, are quantified in toluene equivalents.

The results of the individual substances are calculated in three groups depending on their retention time when analyzing using a non-polar column (HP-1):

- Volatile Organic Compounds (VOC) are defined as: All substances eluting between and including n-hexane (n-C6) and n-hexadecane (n-C16)
- Semi-Volatile Organic Compounds (SVOC) are defined as: All substances eluting after n-hexadecane (n-C16) and before and including n-docosane (n-C22)
- Very Volatile Organic Compounds (VVOC) are defined as: All substances eluting before n-hexane (n-C6).

Total Volatile Organic Compounds (TVOC) is calculated by summation of all individual VOCs with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$ . The TVOC can be expressed either in toluene equivalents as defined in EN 16516 and similar to ISO 16000-6, or as the sum of concentrations using specific or relative response factors. In the case of summation of concentrations using authentic or relative response factors, the toluene equivalent is applied to all non-target and non-identified VOCs before summing up. Compounds regarded as VOC in line with the above definition but elute before n-C6 or after n-C16 on the HP-5 column are treated as VOC, and are thus added to the TVOC.

Total Semi-Volatile Organic Compounds (TSVOC) is calculated by the summation of all individual SVOCs expressed in toluene equivalents with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$ , as defined in EN 16516. VOCs that are regarded as VOC in line with the above definition, but elute after n-C16 in this test, are not added to the TSVOC.

Total Very Volatile Organic Compounds (TVVOC) is calculated by the summation of all individual VVOCs with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$  and expressed in toluene equivalents. VOCs that are regarded as VOC in line with the above definition, but elute before n-C6 in this test, are not added to the TVVOC.

This test only covers substances which can be adsorbed on Tenax TA and can be thermally desorbed. If emissions of substances outside these specifications occur then these substances cannot be detected (or with limited reliability only).

#### 7.5.5 Calculation of R Values with LCI Lists

The concentrations of detected compounds  $\geq 5 \mu\text{g}/\text{m}^3$  are divided by their respective LCI/NIK value (if defined in the given publication). The sum of the quotients gives the R value, which can be mathematically expressed:

$$R = \sum_i^n \left( \frac{c_i}{\text{NIK}_i} + \dots + \frac{c_n}{\text{NIK}_n} \right)$$

This R value is calculated, depending on the purpose of this test, for the European LCI list, for the German LCI/NIK list ( $R_D$ ), and/or for the Belgian LCI list ( $R_B$ ).

All VOCs without published LCI/NIK value and concentration  $\geq 5 \mu\text{g}/\text{m}^3$  are summed up as sum of VOCs without LCI/NIK if required by the standard or protocol.

#### 7.5.6 Testing of Aldehydes

The presence of aldehydes is tested by drawing air samples from the test chamber outlet through DNPH-coated silicagel tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by HPLC and UV-/diode array detection.

The absence of formaldehyde and other aldehydes is stated if UV detector response at the specific wavelength is lacking at the specific retention time in the chromatogram. Otherwise it is checked whether the reporting limit is exceeded. In this case the identity is finally checked by comparing full scan sample UV spectra with full scan standard UV spectra.

#### 7.5.7 Testing of Phthalates

The presence of phthalates is tested by drawing air samples from the test chamber outlet through tube with XAD-II adsorbent after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by GC/MS. Analysis of phthalates is not currently covered by the accreditation (Internal methods no.: 71M549812 / 71M546060).

## 7.6 Quality Assurance

Before loading the test chamber, a blank check of the empty chamber is performed and compliance with background concentrations in accordance with EN 16516 / ISO 16000-9 is determined.

Air sampling at the chamber outlet and subsequent analysis is performed in duplicate. Relative humidity, temperature and air change rate in the chambers is logged every 5 minutes and checked daily. A double determination is performed on random samples at a regular interval and results are registered in a control chart to ensure the uncertainty and reproducibility of the method.

The stability of the analytical system is checked by a general function test of device and column, and by use of control charts for monitoring the response of individual substances prior to each analytical sequence.

## 7.7 Accreditation

The testing methods described above are accredited on line with EN ISO/IEC 17025 by DANAK (no. 522). This accreditation is valid worldwide due to mutual approvals of the national accreditation bodies (ILAC/IAF, see also [www.eurofins.com/galten.aspx#accreditation](http://www.eurofins.com/galten.aspx#accreditation)).

Not all parameters are covered by this accreditation. The accreditation does not cover parameters marked with an asterisk (\*), however analysis of these parameters is conducted at the same level of quality as for the accredited parameters.

## 7.8 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 22%. The expanded uncertainty  $U_m$  equals 2 x RSD. For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

## 7.9 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the “Binary Statement for Simple Acceptance Rule” described in ILAC’s “Guidelines on decision Rules and Statements of Conformity” ILAC-G8:09/2019.

This means that results above the detection limit are always reported with two significant digits. Results are evaluated with the same number of significant digits as the corresponding limit values, and conformity is based on results being less than or equal to limit values.

For limit values with more than two significant digits, the third digit will be used to confirm whether a result is below or equal to the limit value. It will always be indicated in the evaluation table if this expanded evaluation is performed.

For further information please visit [www.eurofins.dk/product-testing/om-os/beslutningsregler/](http://www.eurofins.dk/product-testing/om-os/beslutningsregler/)

## 7.10 Version History

Report date	Report number	Modification
18/02/2022	392-2021-00644701_A_EN	Current version